Product datasheet Intertape® 54108 Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| Intertape® 54108 | | | |
|--|--|--|--|
| Intertape® 54108 consists of a polyester backing with a tightly cured rubber adhesive. | | | |
| Standards | | | |
| UL-File-Nr.: E20780 | | | |
| Delivery forms | | | |
| Width: from 2.5 mm in 0.1 mm increments | | | |
| • Core diameter: 76 mm (3") | | | |
| Special widths on request | | | |
| Color | | | |
| Cream | | | |
| Glue | | | |
| Rubber | | | |
| Adhesive | | | |
| One-sided | | | |
| Storage | | | |

12 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20 $^{\circ}$ C and 50 - 60 $^{\circ}$ C relative humidity. The storage period should not exceed 12 months.







Updated 05/24

SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| General | Unit of measure | |
|----------------------------------|-----------------|------------------|
| Type/ Ordering information | | Intertape® 54108 |
| Standard colours | | cream |
| Backing | | polyester film |
| Backing thickness | mm | 0.025 |
| Adhesive | | rubber |
| Total thickness | mm | 0.061 |
| Electrolyt. corrosion value | | 1.0 Direct/A, 1 |
| Flammability class | | BU 1 |
| Thermal class | | 130 °C (B) |
| Dielectic strength | kV | 5 |
| Tensile strength | N/cm | 44 |
| Adhesiveness / Adhesion to steel | N/cm | 5.5 |
| Elongation at break | % | 100 |
| Insulation resistance | ΜΩ | 10^6 |





