

---

## Extruded Sleeving H

Sleeving H is an extruded silicone sleeving.

---

### Attributes

Sleeving H is flexible, transparent and available in various colours. Due to the silicone rubber coating, this sleeving provides high permanent temperature resistance of class H (180 °C) and thermal resistance up to 200 °C; the special quality version guarantees thermal resistance up to 250 °C.

---

### Application

Sleeving H is used as lightweight, additional mechanical protection for applications with very high thermal stress. Furthermore, it offers additional electrical insulation for cables and enamelled copper wires in electric machines and transformers as well as in certain electronic applications.

---

### Standards

According DIN 60684-3, sheet 123:2001

---

### Delivery forms

Standard: transparent (inner diameter / ID 5)

Special colours on request:

Red, blue, white, black (ID5) and green (ID2)

#### Length in m on a cardboard ring:

0.3 - 2.0 mm 200 m rings/ cardboard spools

2.5 - 3.5 mm 100 m rings/ cardboard spools

4.0 - 9.0 mm 100 m rings

10.0 mm 50 m rings

14.0 - 30.0 mm on request

All dimensions can be delivered in adapted lengths.

| Dimension           | Unit of measure |             |             |             |             |             |             |
|---------------------|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Inner diameter (ID) | mm              | 0.3         | 0.5         | 0.8+        | 1.0         | 1.5         | 2.0         |
| Tolerance (ID)      | mm              | +0.10/-0.05 | +0.15/-0.10 | +0.15/-0.10 | +0.20/-0.15 | +0.20/-0.15 | +0.20/-0.15 |

| Dimension           | Unit of measure |             |             |             |             |             |             |
|---------------------|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Inner diameter (ID) | mm              | 2.5         | 3.0         | 4.0         | 5.0         | 6.0         | 8.0         |
| Tolerance (ID)      | mm              | +0.20/-0.20 | +0.20/-0.20 | +0.20/-0.20 | +0.20/-0.20 | +0.25/-0.25 | +0.25/-0.25 |

| Dimension           | Unit of measure |             |             |             |             |             |             |
|---------------------|-----------------|-------------|-------------|-------------|-------------|-------------|-------------|
| Inner diameter (ID) | mm              | 10.0        | 12.0        | 16.0        | 20.0        | 25.0        | 30.0        |
| Tolerance (ID)      | mm              | +0.25/-0.25 | +0.25/-0.25 | +0.50/-0.50 | +0.50/-0.50 | +0.50/-0.50 | +0.50/-0.50 |

| Wall thicknesses            | Unit of measure |             |           |             |             |             |             |
|-----------------------------|-----------------|-------------|-----------|-------------|-------------|-------------|-------------|
| Wall thickness (wt) nominal | mm              | 0.20        | 0.50      | 0.40        | 0.70        | 1.0         | 1.5         |
| Tolerance (wt)              | mm              | -0.05/+0.15 | 0.05/0.15 | -0.05/+0.15 | -0.05/+0.15 | -0.05/+0.15 | -0.20/+0.20 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.  
Updated 05/24



| Wall thicknesses            | Unit of measure |             |
|-----------------------------|-----------------|-------------|
| Wall thickness (wt) nominal | mm              | 2.0         |
| Tolerance (wt)              | mm              | -0.20/+0.20 |

| Mechanical          | Unit of measure | Values         | Test method  |
|---------------------|-----------------|----------------|--------------|
| Elongation at break | %               | 500 (min. 200) | DIN EN 60684 |
| Tear force          | MPa             | 11 (min. 5.5)  | DIN EN 60684 |

| Thermal           | Unit of measure | Values                                    |
|-------------------|-----------------|---|
| Thermal class     | °C              | 180                                       |
| Application range | °C              | -60 up to 200 (special version up to 250) |

| Electrical                 | Unit of measure          | Conditions       | Values                          | Test method  |
|----------------------------|--------------------------|------------------|---------------------------------|--------------|
| Dielectric strength        | kV                       |                  | appr. 1 / 0.1 mm wall thickness | DIN EN 60684 |
| Specific volume resistance | $\Omega \cdot \text{cm}$ | room temperature | min. $10^{11}$                  | DIN EN 60684 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.  
Updated 05/24



---

| Chemical   | Values             |
|------------|--------------------|
| Resistance | weather, ozone, UV |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.  
Updated 05/24

