
SynTherm® DMD

SynTherm® DMD is a flexible 3-ply insulating material made of polyester film covered with a layer of impregnated fleece on both sides.

Attributes

SynTherm® DMD is a Class F (155 °C) insulating material and has a high dielectric and high mechanical strength. It is tough and flexible.

This allows for easy insertion into the slot and the spreading effect ensures a sturdy grip. The smooth surface makes SynTherm® DMD ideal at automatic insulating and insertion machines. Additionally, it provides excellent adhesion in conjunction with impregnating materials.

The outer cured resin impregnation protects the polyester film against oxidation and hydrolysis.

Application

SynTherm® DMD is used as slot insulation and for pre-shaped wedges in electric motors. Due to its special surface qualities it is also used as phase insulation. SynTherm® DMD is commonly used as core, interlayer und final insulation for the production of transformers.

Standards

- Class F insulating material (155 °C)
- UL approved, e.g. E247773
- Test standard IEC 60626-2
- Sample conditioning acc. to standard atmosphere 23/50

Delivery forms

Total thickness in µm:

100,130, 150, 180, 200, 230, 280, 340, 450

SynTherm® DMD can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness) and above
- in rolls approx. width 1260 mm
- in sheets approx. 630 mm x 800 mm or approx. 800 mm x 1260 mm

Overall diameter of the slit rolls/ rolls as required approx. 240, 330 or 450 mm.

Feathering:

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 07/21



-
- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
 - from widths of 10 to 240 mm and thickness of 0.23 mm
-

Base

PET-film + both sided impregnated non-woven layer

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 07/21



Mechanical	Unit of measure						
Total thickness	mm	0.10	0.13	0.15	0.18	0.20	0.23
Thickness tolerance	%	± 15	± 15	± 15	± 15	± 15	± 15
Specific weight	g/m ²	96	115	145	190	220	260
Film thickness	µm	36	23	50	75	100	125
Tensile strength longitudinal	N/10 mm	60	50	110	140	160	200
Tensile strength transversal	N/10 mm	50	40	90	105	120	150
Elongation at break (unfold) longitudinal	%	20	20	20	20	20	20
Elongation at break (unfold) transversal	%	50	50	50	50	50	50

Mechanical	Unit of measure			
Total thickness	mm	0.28	0.34	0.45
Thickness tolerance	%	± 15	± 10	± 10
Specific weight	g/m ²	350	425	560
Film thickness	µm	190	250	350

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 07/21



Mechanical	Unit of measure			
Tensile strength longitudinal	N/10 mm	300	350	400
Tensile strength transversal	N/10 mm	200	300	350
Elongation at break (unfold) longitudinal	%	20	20	20
Elongation at break (unfold) transversal	%	50	50	50

Electrical	Unit of measure						
Total thickness	mm	0.10	0.13	0.15	0.18	0.20	0.23
Dielectric strength (unfold)	kV	4.5	4	6	7	9	10

Electrical	Unit of measure			
Total thickness	mm	0.28	0.34	0.45
Dielectric strength (unfold)	kV	15	18	22

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 07/21

