
SynTherm® VPV

SynTherm® VPV is a flexible 3-ply insulating material made of polyester film with a layer of polyester non-woven on both sides.

Attributes

SynTherm® VPV is an insulating material without additional impregnants, which can be used for insulation class F (155 °C) systems after through impregnation with varnishes or resins of the corresponding insulation class. The ability of the non-woven layers to absorb impregnants results in outstanding saturation of the slot surfaces and exceptional bonding of all winding components with the laminated core.

SynTherm® VPV is characterised by its high resistance to moisture and chemicals and excellent dielectric strength. The smooth surface of the SynTherm® VPV makes the material ideal for machining.

Application

SynTherm® VPV is used as slot insulation and phase insulation in electric machines. SynTherm® VPV is used as interlayer insulation and final insulation in transformers.

Standards

- Suitable for insulation class F 155 °C systems after impregnation with high quality class F or H varnishes or resins (file-no. E247773)

Delivery forms

Film thickness in µm:

90, 120, 150, 180, 200, 230, 300, 350, 450

SynTherm® VPV can be supplied:

- in slit rolls from widths of 10 mm and above
- in rolls approx. 630 mm or 1,260 mm
- in sheets approx. 630 mm x 800 mm or
approx. 800 mm x 1,260 mm

Feathering:

- depth approx. 1 - 12 mm, distance approx. 1 - 10 mm
- from widths of 10 to 240 mm and thickness of 0.23 mm

Base

PET-film + polyester non-woven on both sides

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 06/24



Mechanical	Unit of measure						
Nominal thickness	mm	0.09	0.12	0.15	0.18	0.20	0.23
Typical thickness	mm	0.09	0.12	0.15	0.18	0.20	0.23
Thickness tolerance max.	%	±15	± 15	± 15	± 15	± 15	± 15
Specific weight	g/m ²	80	115	145	190	220	260
Film thickness	µm	23	23	50	75	100	125
Elongation at break (unfold) longitudinal	%	15	20	20	20	20	20
Elongation at break (unfold) transversal	%	50	50	50	50	50	50
Tensile strength longitudinal	N/10 mm	50	50	110	140	160	200
Tensile strength transversal	N/10 mm	40	40	90	105	120	150

Mechanical	Unit of measure			
Nominal thickness	mm	0.28	0.34	0.45
Typical thickness	mm	0.30	0.35	0.45

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 06/24



Mechanical	Unit of measure			
Thickness tolerance max.	%	± 15	± 10	± 10
Specific weight	g/m ²	350	425	560
Film thickness	µm	190	250	350
Elongation at break (unfold) longitudinal	%	20	20	20
Elongation at break (unfold) transversal	%	50	50	50
Tensile strength transversal	N/10 mm	200	300	350
Tensile strength longitudinal	N/10 mm	300	350	400

Electrical	Unit of measure						
Nominal thickness	mm	0.09	0.12	0.15	0.18	0.20	0.23
Dielectric strength (unfold)	kV	4	4	6	7	9	10

Electrical	Unit of measure			
Nominal thickness	mm	0.30	0.35	0.45
Dielectric strength (unfold)	kV	15	18	22

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 06/24

