
SHTherm® 210 Alu

- Enamelled al.wire
- Insulated with theic-mod. polyesterimide and amid-imid topcoat
- Class 200

Attributes

SHTherm® 210 AL is a highly thermo-resistant enamelled aluminium wire of heat performance class N with a wide range of good and very good quality features. As it is a dual-coat wire its insulation film consists of two different coatings on top of one another. These ensure: a very good permanent thermal and overload resistance, excellent esistance to chemical attacks e.g. by alkalines, washing and cleaning agents, impregnating varnishes and resins, sealing compounds, thinners, solvents and refrigerants as well as their vapours, an excellent mechanical abrasion resistance.

On demand the system can be offered with an additional layer of selflubricating enamel thus giving enhanced properties for winding operations.

Application

Control gears, drives for household equipment, electric motor drives, pump drives, refrigerators, transformers

Standards

IEC /DIN EN 60317-25

NEMA MW 35-A / 73-A

UL approved

Delivery forms

Grade 1: 1.250 - 4.000 mm

Grade 2: 1.250 - 4.000 mm

< 1.250 mm on request

> 4.000 mm on request

Typical properties of enamelled round aluminium wire 0.600 m, with insulation film grade 1

Mechanical	Unit of measure	Set value	Actual value
Outer diameter with varnish	mm	min. 0.627 - max. 0.649	as set value
Bare wire diameter	mm	0.594-0.606	as set value
Elongation and adhesion		3 x d	2 x d
Scrape resistance	N	≥ 2,2	≥ 3.5
Pencil hardness of varnish		H	4H - 5H
Elongation at break	%	≥ 12	≥ 20
Coefficient of friction	μ	/	≤ 0.140

Thermal	Unit of measure	Set value	Actual value
Temperature index	°C	200	207
Cut through temperature (pre-heated block)	°C	/	/
Dielectric loss factor (bending point)	(°C) (tan δ)	/	≥ 185
Heat shock at 220 °C (no cracks in varnish coat after winding)		3 x d	3 x d
Solderability		no	no

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 05/18



Electrical	Unit of measure	Set value	Actual value
Dielectric strength RT	kV	≥ 2.6 (twist)	≥ 3 (cylinder)
High voltage discontinuities 1000V		≤ 25 on 30 m	≤ 7 on 100 m
Electrical conductivity	MS/m	35.5 - 36.2	≥ 35.85

Chemical	Set value	Actual value
Pencil hardness (storage in standard solvent ½ h / 60 °C)	min. H	3H - 5H
Pencil hardness (storage in alcohol ½ h / 60 °C)	min. H	3H - 5H
Resistance to commercial impregnants ⁽¹⁾	/	yes
Resistance to commercial refrigerants (1)	/	yes
Resistance to dry transformer oils (1)	/	yes
Resistance to hydraulic oils (1)	/	yes

(1) Due to the variety of individual applications we cannot make any generally binding commitments regarding the compatibility. We recommend testing compatibility with the materials being used.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 05/18

