Product datasheet SynTape® F/ K.30AC Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



SynTape® F/ K.30AC

SynTape[®] F/ K.30AC is a polyethylene naphthalate (TEONEX[®]) adhesive tape with good adhesiveness due to thermosetting acrylate adhesive.

Attributes

The tape is characterised by its enhanced property level in contrast to common PET adhesive tapes.

Application

As core and interlayer insulation, final insulation, and taping and insulation of coils and wires.

Delivery forms

• Width: From 2.5 mm, in 0.1 mm increments

Standard length: 66 m
Core diameter: 76 mm (3")
Special widths on request

Glue

Acrylate

Adhesive

one-sided

Storage

6 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20 °C and 50 - 60 % relative humidity. The storage period should not exceed 6 months.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 01/17

 $\label{tensor} \mbox{Teonex} \mbox{$\$$ is a registered trademark of TOYOBO CO., Ltd.}$







SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



General	Unit of measure	
Type/ Ordering information		F/ K.30AC
Standard colours		transparent
Backing		TEONEX®
Backing thickness	mm	0.025
Adhesive		Acrylate
Thermal class		155 °C/ F
UL FILE NO.		E 178 430
Total thickness	mm	0.060
Tensile strength	N/cm	40
Elongation at break	%	50
Adhesiveness / Adhesion to steel	N/cm	5.0
Dielectic strength	kV	6.0
Electrolyt. corrosion value		1





