SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



3M[™] no. 79

3M electro-insulating tape No. 79 is a UL-approved fibre glass adhesive tape with acrylate adhesive.

Attributes

High tear and temperature resistant fabric tape with good varnish and resin resistance. Very easy to form!

Application

As electrical insulation of coils and transformers, as final insulation and as coil ends of stators. It is used if high mechanical strength, stress relief and thermal resistance are required.

Standards

Delivery forms

- Width: From 2.5 mm, in 0.1 mm increments
- Standard length: 55 m
- Core diameter: 76 mm (3")
- Special widths on request

Glue

Acrylate

Adhesive

one-sided

Storage

Adhesive tapes should always be stored in a cool, dry place at approx. 20 °C and 50 - 60 % relative humidity. The storage period should not exceed 6 months.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 05/24



SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



General	Unit of measure	
Standard colours		White
Type/ Ordering information		3M™ electro-insulating tape no. 79
Backing		Glass fibre
Backing thickness	mm	0.127
Adhesive		Acrylate
Thermal class		155 °C
Electrolyt. corrosion value		A 0.9
UL FILE NO.		E 17385 OANZ 2
Dielectic strength	kV	3
Adhesiveness / Adhesion to steel	N/cm	3.3
Elongation at break	%	5
Tensile strength	N/cm	262
Total thickness	mm	0.177

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 05/24

