
Intertape® 54108

Intertape® 54108 consists of a polyester backing with a tightly cured rubber adhesive.

Standards

UL-File-Nr.: E20780

Delivery forms

- Width: from 2.5 mm in 0.1 mm increments
- Core diameter: 76 mm (3")
- Special widths on request

Color

Cream

Glue

Rubber

Adhesive

One-sided

Storage

12 months at room temperature. Adhesive tapes should be stored in a cool, dry place at approx. 20 °C and 50 - 60 % relative humidity. The storage period should not exceed 12 months.

| General | Unit of measure | |
|----------------------------------|-----------------|------------------|
| Type/ Ordering information | | Intertape® 54108 |
| Standard colours | | cream |
| Backing | | polyester film |
| Backing thickness | mm | 0.025 |
| Adhesive | | rubber |
| Total thickness | mm | 0.061 |
| Electrolyt. corrosion value | | 1.0 Direct/A, 1 |
| Flammability class | | BU 1 |
| Thermal class | | 130 °C (B) |
| Dielectric strength | kV | 5 |
| Tensile strength | N/cm | 44 |
| Adhesiveness / Adhesion to steel | N/cm | 5.5 |
| Elongation at break | % | 100 |
| Insulation resistance | MΩ | 10 ⁶ |
| UL FILE NO. | | E20780 |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 05/24

Intertape® is a registered trademark of Intertape Polymer Group.

