**Product datasheet** SynTape® 6455 Page 1 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



# SynTape® 6455

### **Attributes**

SynTape® 6455 is used by our customers especially for phase insulation. The structure of rubber adhesive (very good adhesion to enamelled copper wire) with liner enables perfect preparation for assembly. The carrier made of aramid paper and PI film ensures high temperature resistance combined with high mechanical and electrical strength.

### **Application**

Phase insulation

### **Delivery forms**

Width: from 12 to 300 mm (smaller dimensions require an internal check)

Standard length: 50 m (special lengths up to 300 m are possible - depending on the width)

Core diameter: 76 mm (3")

#### Glue

Rubber

## Storage

Adhesive tapes should always be stored in a cool and dry place at approx. 20-30°C and below 50% relative humidity. The storage time should generally not exceed 6 months.

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 10/24

SynTape® is a registered trademark of SynFlex.





**Product datasheet** SynTape® 6455 Page 2 SynFlex Elektro GmbH Auf den Kreuzen 24 D-32825 Blomberg Germany Telefon +49-5235-968-0 E-Mail info@synflex.de



| General                         | Unit of measure |  |
|---------------------------------|-----------------|--|
| Type/ Ordering information      |                 | 6455                                       |
| Backing                         |                 | 50 μm aramide papier, 25 μm polyimide film |
| Adhesive                        |                 | rubber                                     |
| Total thickness                 |                 | 135 μm                                     |
| Backing thickness               | mm              | 80 μm                                      |
| Liner                           |                 | Siliconised paper                          |
| Adhesiveness / steel            | N               | 5.8 / 10 mm                                |
| Tear force in machine direction | N               | 82 / 10 mm                                 |
| Dielectric strength             | kV              | 7  |

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet. Updated 10/24

SynTape® is a registered trademark of SynFlex.



