
SynKraft® E

A high-quality insulating material based on calandered 100 % unbleached sulphate wood pulp.

Attributes

SynKraft® E displays excellent flexibility, good tensile and compressive strength, good compatibility with dip and trickle resins and good impregnating properties.

Application

Pressboard is a classic insulating material for electrical equipment and is commonly used in transformers, but also in electrical motors at reduced thermal loads.

Application ranges from slot insulation for stators and rotors, through wedges in electric motors to core, interlayer and final insulation for transformers.

Standards

- Class A (105 °C) insulating material
- Test standard IEC 60641-2
- Sample conditioning according to standard atmosphere 23/50

Delivery forms

Total thickness in µm:

- rolls (PSP E3040) 100, 150, 200, 250, 300, 400, 500, 800, 1000
- formats (PSP E3030) 0.1 to 3.0 mm

SynKraft® E can be supplied:

- in slit rolls from widths of 6 mm (depending on thickness)
- in rolls (PSP E3040) in widths of approx. 640 or 1280 mm
- overall diameter of the slit rolls / rolls is optionally approx. 240, 330 or 450 mm
- in formats (PSP E3030) depending on the thickness 640 x 800 mm or 800 x 1280 mm, other formats are available on request

Feathering:

- depth approx. 1 to 12 mm, distance approx. 1 to 10 mm
- from widths of 10 to 240 mm and up to thickness of 0.35 mm

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.

Updated 06/19

SynKraft® is a registered trademark of SynFlex.



Mechanical	Unit of measure	SynKraft® E3030 (formats)	SynKraft® E3040 (rolls)
Thickness tolerance	%	±10	±10
Density	g/cm ³	1.20	1.20
Tensile strength (unfold) longitudinal	N/mm ²	80	80
Tensile strength (unfold) transversal	N/mm ²	45	45
Elongation at break (unfold) longitudinal	%	3	3
Elongation at break (unfold) transversal	%	9	9
Shrinkage longitudinal	%	0.7	0.7
Shrinkage transversal	%	1.2	1.2
Combustion residue	max. %	0.5	0.5
Moisture content	max. %	8	8

Electrical	Unit of measure	SynKraft® E 3030 (formats)	SynKraft® E3040 (rolls)
Dielectric strength	kV/mm	11	11

The information on this data sheet is based on the information provided by our supplier. It does not represent any specification or agreements regarding conditions or properties. The indicated values are standard values. Deviations from those values due to production and application cannot be excluded. The information on this data sheet is addressed to experts who use it at their own discretion and at their own risk. We do not guarantee results, or accept liability for the indicated specifications or for results obtained based on the specifications. Please contact us for more detailed information. Non-toxic and toxic substances are listed on the safety data sheet.
Updated 06/19

SynKraft® is a registered trademark of SynFlex.

